


CLAIMS

Sub 7
B2


1) A cement slurry intended to be set in a wellbore through at least one geologic formation having a certain permeability, characterized in that it comprises cement, at least one mineral filler, water and a determined amount of at least one polymer with hydrophilic (Hy) and hydrophobic (Hb) units in aqueous solution, said hydrophobic units (Hb) containing C1-C30 alkyl, aryl or alkyl-aryl groups, said polymer having the following structure : —(Hb)—(Hy)— with a statistical distribution, and :

- Hy has the following form :



where R5 is H or CH₃, and Z1 is COOH or CONH₂ or CONHR¹SO₃⁻, or CONHR¹, R¹ is CH₃ ;

- Hb has the following form :



where R'5 is H or CH₃ and Z2 is COOR⁷, C₆H₄SO₃H, COOR¹, CONR¹R¹ or CONR¹R⁷, R⁷ being a non-ionic surfactant consisting of an alkyl polyoxyethylene chain, R¹ is H or a C1-C30 alkyl, aryl or alkyl-aryl radical, and R¹ is a C1-C30 alkyl, aryl or alkyl-aryl radical.

2) A slurry as claimed in claim 1, wherein said polymer has a molecular mass ranging between 10^4 and 10^7 daltons and a proportion of hydrophobic units Hb ranging between 0.5 and 60 %.

Sub B 2 cont.
A 3) A slurry as claimed in ~~any one of the previous claims~~ ^{claim 1}, comprising at least one of the polymers selected from the group consisting of:

- HMPAM, where R5 is H and Z1 is CONH2, R'5=CH3 and Z2 is COOR'1 with R'1=C9H19,
- S1, S2 where R5 is H and Z1 is CONH2, R'5=H and Z2 is C6H4SO3H,
- Hb1 where R5 is H, Z1 is COOH, R'5 is H and Z2 is COOR'1 with R'1 being C4.


claim 1
A 4) A slurry as claimed in ~~any one of the previous claims~~, wherein the mineral filler consists of silica whose grain size ranges between 5 and 200 μm and microsilica whose grain size ranges between 0.1 and 20 μm .

Sub C4
5) A slurry as claimed in claim 3, wherein said polymer S1 or S2 is combined with polymer HMPAM.

15 6) A slurry as claimed in claim 3, wherein said polymer is Hb1 at a concentration ranging between 0.5 and 5 % by weight.

7) An additive for cement slurry, characterized in that it essentially comprises a polymer with hydrophilic (Hy) and hydrophobic (Hb) units in aqueous solution, said hydrophobic units (Hb) containing C1-C30 alkyl, aryl or alkyl-aryl groups, said
20 polymer having the following structure :

- Hy has the following form :




5

where R5 is H or CH3, and Z1 is COOH or CONH2 or CONHR1SO3⁻, or CONHR''1, R''1 is CH3 ;

- Hb has the following form :

10



where R'5 is H or CH3 and Z2 is COOR7, C6H4SO3H, COOR'1, CONR1R'1 or
 15 CONR1R7, R7 being a non-ionic surfactant consisting of an alkyl polyoxyethylene
 chain, R1 is H or a C1-C30 alkyl, aryl or alkyl-aryl radical, and R'1 is a C1-C30 alkyl,
 aryl or alkyl-aryl radical.

Add 7
B³

Add C6